

AMENDMENTS TO THE CLAIMS


This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1-55 (canceled)

56. (previously presented) A polymer film comprising:

(i) a treated pigment, wherein said treated pigment comprises titanium dioxide and an organo-phosphoric acid compound having the formula:



wherein  $n = 4-14$ , and each  $R'$  is an organic group having from 2 to 22 carbon atoms or hydrogen and within any one molecule, any two or more  $R'$  groups may be the same provided that at least one of the  $R'$  groups is not hydrogen; and

(ii) a polymer,

wherein said organo-phosphoric acid compound is present in an amount from about 0.01 percent to about 5 percent by weight, based on the weight of the titanium dioxide, and said treated pigment is present in an amount of about 20 wt. % based on the weight of the polymer film.

57. (previously presented) The polymer film of claim 56, wherein said polymer is polyethylene.


58. (canceled)

59. (canceled)

60. (previously presented) The polymer film of claim 56 further comprising an additional metal oxide selected from the group consisting of aluminum oxide, silicon dioxide and zirconium oxide.

61. (previously presented) A polymer film comprising:

(i) a treated pigment, wherein said treated pigment comprises titanium dioxide and an organo-phosphoric acid compound having the formula:



wherein  $n = 4-14$ , and each  $R'$  is an organic group having from 2 to 22 carbon atoms or hydrogen and within any one molecule, any two or more  $R'$  groups may be the same provided that at least one of the  $R'$  groups is not hydrogen; and

(ii) a polymer, wherein said polymer comprises polyethylene, wherein said organo-phosphoric acid compound is present in an amount from about 0.01 percent to about 5 percent by weight, based on the weight of the titanium dioxide, and wherein said treated pigment is present in an amount of about 20 wt. % based on the weight of the polymer film.

62. (previously presented) A polymer film comprising:

(i) a treated pigment, wherein said treated pigment comprises titanium dioxide and an organometaphosphate compound having the formula:



wherein  $m = 1-14$ , and each  $R''$  is an organic group having from 2 to 22 carbon atoms or hydrogen and within any one molecule, any two or more  $R''$  groups may be the same provided that at least one of the  $R''$  groups is not hydrogen; and

(ii) a polymer, wherein said organometaphosphate compound is present in an amount from about 0.01 percent to about 5 percent by weight, based on the weight of the titanium dioxide, and said treated pigment is present in an amount of about 20 wt. % based on the weight of the polymer film.

63. (previously presented) The polymer film of claim 62, wherein said polymer is polyethylene.

64. (canceled)

65. (canceled)

66. (previously presented) The polymer film of claim 62 further comprising an additional metal oxide selected from the group consisting of aluminum oxide, silicon dioxide and zirconium oxide.

67. (previously presented) A polymer film comprising:

(i) a treated pigment, wherein said treated pigment comprises titanium dioxide and an organometaphosphate compound having the formula:



wherein  $m = 1-14$ , and each  $R''$  is an organic group having from 2 to 22 carbon atoms or hydrogen and within any one molecule, any two or more  $R''$  groups may be the same provided that at least one of the  $R''$  groups is not hydrogen; and

(ii) a polymer, wherein said polymer comprises polyethylene, wherein said organometaphosphate compound is present in an amount from about 0.01 percent to about 5 percent by weight, based on the weight of the titanium dioxide, and wherein said treated pigment is present in an amount of about 20 wt. % based on the weight of the polymer film.

68-70 (canceled)